

Manufacturer: Taita Chemical Company, Limited



(General Purpose Polystyrene) GPPS 861N / B

Characteristics	Applications
- Injection Grade - The most state-of-the-art form US NOVA CHEMICAL - Low Residual Monomer - Good Heat Resistance - Mold Dimension Stability - Good Transparency - Easy Processing	- Electrical appliances - house hard wares - cassette & cosmetic cases - lamp decoration - toys.

Physical Properties				
Properties	ASTM method	Test Condition	Unit	Typical Value
Specific Gravity	D542	---	---	1.046
Melt Flow Index	D1238	200°C, 5 kg load	g/10min	7.0
Tensile Strength at Yield	D638	23°C, 1/8" Sample	kg/cm2	450
Elongation at Break	D638	23°C, 1/8" Sample	%	2.0
Izod Impact Strength	D256	23°C, A method, notched 1/4"×1/2"×5/2"	kg-cm/cm	1.4
Vicat Softening Temperature	D1525	1 kg load, 3 mm Thick (120 °C/hr)	°C	100
Flammability	UL-94	1/16" Sample	File No. E50263	94HB
Residual SM monomer	Internal	GC	ppm	< 300
Haze	---	2.8mm thick	%	0.4

EGYPTIAN SAUDI COMPANY FOR PLASTIC

Address: office 307-mall el marwa- ordonya area-10th of ramadan city-sharqia -Egypt

C.R: 122055

Mobile : 01068993789

Email: info@dagplast.com