

Manufacturer: CHI MEI CORPORATION

CHIMEI

Oil-extended TPE KIBITON® Characteristics PB-585

PROPERTIES	TEST METHOD	TEST CONDITION	UNIT	OIL-EXTENDED
				PB-585
BD/SM	ASTM D5775	-	%	68/32
Volatile matter	ASTM D5668	-	wt%	0.6
Ash Content	ASTM D5667	-	wt%	0.3
Oil Content	ASTM D5774	-	wt%	31
Melt Flow Index	ASTM D1238	190 °C, 5 Kg	g/10 min	8
Hardness	ASTM D2240	-	Shore-A	47
Specific Gravity	ASTM D792	23 °C	-	0.94

EGYPTIAN SAUDI COMPANY FOR PLASTIC

Address: office 307-mall el marwa- ordonya area-10th of ramadan city-sharqia -Egypt

C.R: 122055

Mobile : 01068993789

Email: info@dagplast.com